

|                  |                       |
|------------------|-----------------------|
| GRADE            | (EK-1108)             |
| STANDARD OF TEST | Q/320412 CNW 002-2015 |

|                  |     |     |       |                |
|------------------|-----|-----|-------|----------------|
|                  |     |     | 71.4  | GB/T 6343-2009 |
| TENSILE STRENGTH | Kpa | 50  | 161.5 | GB/T 6344-2008 |
| TENSILE RATE     | %   | 150 | 176   | GB/T 6344-2008 |

|                                |     |     |     |                |
|--------------------------------|-----|-----|-----|----------------|
| 50%<br>COMPRESSION DEFORMATION | %   | 30  | 9.0 | GB/T6669-2008  |
| TEARING STRENGTH               | N/m | 300 | 390 | GB/T10808-2006 |
|                                |     |     |     |                |