

GRADE		CR-2016		
STANDARD OF TEST		Q/320412 CNW 002-2015		
DENSITY	Kg/m ³	160	184.3	GB/T 6343-2009
TENSILE STRENGTH	Kpa	≥ 1000	1364.0	GB/T 6344-2008
TENSILE RATE	%	≥ 100	239.6	GB/T 6344-2008
COMPRESSION DEFLECTION	Kpa	≥ 40	52.7	ASTM D 1056
COMPRESSION DEFORMATION	%	≤ 30	18.6	GB/T6669-2008
TEARING STRENGTH	N/m	≥ 1200	1598	GB/T10808-2006
OXYGEN INDEX	%	≥ 26	26.1	GB/T 2406-2009
HARDNESS	°	15-25	15	C
105 ±3 7d	%	≤ 10.0	9.3	GB/T 17794-2008
-40 ±3 5h	--			GB/T 17794-2008